



# PASARGAD POLYMER PEYVAND CO

**Grade :** Pasamid 3P-H1000B

General	
Manufacturer / Supplier	Pasargad Polymer Peyvand Co.(3P)
Generic Symbol	Polyamide 6 (Nylon 6)
Filler / Reinforcement	.....
Color	Black
Forms	Pellets
Processing Method	Injection Molding
Uses	Automotive Application Furniture Appliance Components Electrical Parts Fastener Housing

Physical	Test Method	Unit	Value
Density	ISO 1183	g/cm3	1.14

Mechanical	Test Method	Unit	Value
Tensile Modulus	ISO 527-2	Mpa	3750
Tensile Stress (Break)	ISO 527-2	Mpa	70
Tensile Strain (Break)	ISO 527-2	%	40<

Impact	Test Method	Unit	Value
Charpy Notched Impact Strength 23 oC	ISO 179/1eA	KJ/m2	20
Charpy Unnotched Impact Strength 23 oC	ISO 179/1eU	KJ/m2	NB

Thermal	Test Method	Unit	Value
Heat Deflection Temperature 1.8 Mpa, Unannealed	ISO 75-2/C	oC	65
Melting Temperature	ISO 11357-3	oC	220

Injection	Nominal Value	Unit
Drying Temperature	90	
Drying Time	2-4 hr	
Rear Temperature	230-250	

## Pasargad Polymer Peyvand

Office : 3rd section , No.32 , Mohamadi Alley , Golbar St., Tohid Sq., Tehran,Iran  
 Tel/Fax : +98-21-66565991/3  
 Factory : No.F21 , Kosar Industrial Area , Eshtehard-Maahdasht Road , Alborz , Iran  
 Tel/Fax : +98-263-7360980/3

