



PASARGAD POLYMER PEYVAND CO

Grade : Pasalac 3P-H9000W

General

Manufacturer / Supplier	Pasargad Polymer Peyvand Co.(3P)
Generic Symbol	Acrylonitrile butadiene styrene (ABS)/polycarbonate(PC)
Filler / Reinforcement
Color	White
Forms	Pellets
Processing Method	Injection Molding
Uses	Automotive Application Furniture Appliance Components Automotive Exterior Parts Automotive Interior Parts

Physical		Unit	Value	
Density	ISO 1183	g/cm ³	1.16	---
Melt Mass-Flow Rate (MFR) (230oC/2.16 kg)	ISO 1183	gr/10 min	5	

Mechanical	Test Method	Unit	Value
Tensile Modulus	ISO 527-2	Mpa	2800
Tensile Stress (Break)	ISO 527-2	Mpa	50
Tensile Strain (Break)	ISO 527-2	%	60

Impact	Test Method	Unit	Value
Charpy Notched Impact Strength 23 oC	ISO 179/1eA	KJ/m ²	60
Charpy Unnotched Impact Strength 23 oC	ISO 179/1eU	KJ/m ²	NB

Thermal	Test Method	Unit	Value
Heat Deflection Temperature 1.8 Mpa, Unannealed	ISO 75-2/C	oC	110
Melting Temperature	ISO 11357-3	oC	230

Injection	Nominal Value	Unit
Drying Temperature	
Drying Time	
Rear Temperature	

Pasargad Polymer Peyvand

Office : 3rd section , No.32 , Mohamadi Alley , Golbar St., Tohid Sq., Tehran,Iran
 Tel/Fax : +98-21-66565991/3
 Factory : No.F21 , Kosar Industrial Area , Eshtehard-Maahdasht Road , Alborz , Iran
 Tel/Fax : +98-263-7360980/3